

# LNPT<sup>™</sup> FARADEx<sup>™</sup> COMPOUND AS002

AS-1002  
REGION ASIA

## DESCRIPTION

LNPT<sup>™</sup> FARADEx<sup>™</sup> AS002 is a compound based on ABS resin containing 10% Stainless Steel. Added features of this material include: Electrically Conductive, EMI/RFI Shielding.

## TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yield	42	MPa	ASTM D 638
Tensile Stress, break	39	MPa	ASTM D 638
Tensile Strain, yield	2.2	%	ASTM D 638
Tensile Strain, break	8.6	%	ASTM D 638
Tensile Modulus, 50 mm/min	2990	MPa	ASTM D 638
Flexural Stress	75	MPa	ASTM D 790
Flexural Modulus	2810	MPa	ASTM D 790
Tensile Stress, yield	39	MPa	ISO 527
Tensile Stress, break	37	MPa	ISO 527
Tensile Strain, yield	2.2	%	ISO 527
Tensile Strain, break	3.3	%	ISO 527
Tensile Modulus, 1 mm/min	2500	MPa	ISO 527
Flexural Stress	66	MPa	ISO 178
Flexural Modulus	2500	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	286	J/m	ASTM D 4812
Izod Impact, notched, 23°C	58	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	11	J	ASTM D 3763
Izod Impact, unnotched 80°10°4 +23°C	20	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	7	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL</b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	97	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	87	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.92E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.56E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	7.8E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	9.6E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80°10°4 sp=64mm	91	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80°10°4 sp=64mm	78	°C	ISO 75/Af
<b>PHYSICAL</b>			
Density	1.12	g/cm <sup>3</sup>	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.2	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	18	%	ASTM D 955

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage, xflow, 24 hrs	27	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs	0.18	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.27	%	ISO 294
Density	1.11	g/cm <sup>3</sup>	ISO 1183
<b>ELECTRICAL</b>			
Volume Resistivity	100 – 1000000	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+01 – 1.E+05	Ohm	ASTM D 257
Shielding Effectiveness @ 3mm	40 – 55	dB	SABIC method
<b>INJECTION MOLDING</b>			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.05 – 0.1	%	
Melt Temperature	240 – 255	°C	
Front - Zone 3 Temperature	255 – 265	°C	
Middle - Zone 2 Temperature	230 – 245	°C	
Rear - Zone 1 Temperature	210 – 220	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.