

# LNP<sup>TM</sup> LUBRICOMP<sup>TM</sup> COMPOUND RFL36L

RFL-4036 LE

## DESCRIPTION

LNP LUBRICOMP RFL36L is a compound based on Nylon 66 resin containing 30% Glass Fiber, 15% PTFE. Added features of this material include: Wear Resistant, Low Extractible.

## TYPICAL PROPERTY VALUES

Revision 20200205

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yield	151	MPa	ASTM D 638
Tensile Stress, break	151	MPa	ASTM D 638
Tensile Strain, yield	2.8	%	ASTM D 638
Tensile Strain, break	2.8	%	ASTM D 638
Tensile Modulus, 50 mm/min	10340	MPa	ASTM D 638
Flexural Stress	213	MPa	ASTM D 790
Flexural Modulus	8270	MPa	ASTM D 790
Tensile Stress, yield	152	MPa	ISO 527
Tensile Stress, break	152	MPa	ISO 527
Tensile Strain, yield	2.8	%	ISO 527
Tensile Strain, break	2.8	%	ISO 527
Tensile Modulus, 1 mm/min	10050	MPa	ISO 527
Flexural Stress	230	MPa	ISO 178
Flexural Modulus	9300	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	1009	J/m	ASTM D 4812
Izod Impact, notched, 23°C	96	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	12	J	ASTM D 3763
Multiaxial Impact	2	J	ISO 6603
Izod Impact, unnotched 80°10°4 +23°C	61	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	10	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL</b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	261	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	252	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.38E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	2.88E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	7.4E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	2.9E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80°10°4 sp=64mm	260	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80°10°4 sp=64mm	247	°C	ISO 75/Af
<b>PHYSICAL</b>			
Density	1.52	g/cm <sup>3</sup>	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.4	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	0.4 – 0.6	%	ASTM D 955

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage, xflow, 24 hrs	1.3 – 1.5	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs	0.53	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	1.4	%	ISO 294
Wear Factor Washer	4	10 <sup>-4</sup> in <sup>3</sup> -min/ft-lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.66	-	ASTM D 3702 Modified: Manual
Static COF	0.65	-	ASTM D 3702 Modified: Manual
Density	1.52	g/cm <sup>3</sup>	ISO 1183
<b>INJECTION MOLDING</b>			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	280 – 305	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.