

LNPTM LUBRICOMPTM COMPOUND RFL36XXZ

RFL-4036
REGION ASIA

DESCRIPTION

LNP LUBRICOMP RFL36XXZ is a compound based on Nylon 66 resin containing 30% Glass Fiber, 15% PTFE. Added feature of this material is: Wear Resistant.

TYPICAL PROPERTY VALUES

Revision 20200317

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	139	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.1	%	ASTM D 638
Tensile Modulus, 50 mm/min	11230	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	236	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	9750	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	138	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.1	%	ISO 527
Tensile Modulus, 1 mm/min	9800	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	211	MPa	ISO 178
Flexural Modulus, 2 mm/min	9700	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	907	J/m	ASTM D 4812
Izod Impact, notched, 23°C	106	J/m	ASTM D 256
Izod Impact, unnotched 80*10*4 +23°C	51	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	10	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	248	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.8E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	5.58E-05	1/°C	ASTM E 831
CTE, 23°C to 60°C, flow	3.78E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	5.5E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	248	°C	ISO 75/Af
Relative Temp Index, Elec ⁽¹⁾	120	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	65	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	65	°C	UL 746B
PHYSICAL			
Density	1.51	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.62	%	ASTM D 570
Dynamic COF	0.58	-	ASTM D 3702 Modified: Manual
Static COF	0.49	-	ASTM D 3702 Modified: Manual
Density	1.51	g/cm ³	ISO 1183
Mold Shrinkage, flow, 24 hrs	0.2 – 0.5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.8 – 1.2	%	ASTM D 955

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E207780-101282824	-	-
UL Recognized, 94HB Flame Class Rating	≥0.75	mm	UL 94
INJECTION MOLDING			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	280 – 305	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.