

SILTEM™ RESIN HUSTM1500

DESCRIPTION

SILTEM™ HUSTM1500 resin is a flexible polyetherimide(PEI)-siloxane copolymer. The intended use for this material is in medical devices and pharmaceutical applications. The material is biocompatible (ISO 10993) and Healthcare management of change applies. The material is RoHS compliant and offers a halogen free (according VDE 0472) flame retardant solution that also offers low smoke emission and toxicity. It is an amber colored transparent material that can be self-colored and easily processed on conventional processing equipment. The material may be used for extrusion of e.g. tubing, catheters, cannulas, as well as flexible injection molded parts.

ISCC+ certified renewable bio-based solutions can be made available for this grade.

The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

| GENERAL INFORMATION | |
|-----------------------|--|
| Applications | Healthcare, Pharmaceutical Packaging & Drug Delivery, Surgical Devices, healthcare device |
| Features | Flame Retardant, Chemical Resistance, Good Processability, High Flow, Low Smoke and Toxicity, Thin Wall, Dielectrics, Amorphous, Healthcare, Flexible, Low Corrosivity, IR Transparent, Low Moisture Absorption, Low Specific Gravity, Sustainable (bio-based offerings), Transparent/Translucent, Biocompatibility-ISO10993, Healthcare/Formula lock, Non Cl/Br flame retardant, Non halogenated flame retardant, Dimensional stability, High temperature resistance, No PFAS intentionally added |
| Fillers | Unreinforced |
| Brands | SILTEM™ |
| Polymer Types | Polyetherimide (PEI) |
| Processing Techniques | Compounding Extrusion, Film Extrusion, Injection Molding, Profile Extrusion, Extrusion, Compression molding, Injection compression molding, Pipe extrusion, Foam Extrusion |
| Regional Availability | Global |

| INDUSTRY | SUB INDUSTRY |
|------------------------|---|
| Hygiene and Healthcare | Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing |

TYPICAL PROPERTY VALUES

Revision 20260326

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|----------------|-----------|--------------|
| MECHANICAL | | | |
| Taber Abrasion, CS-17, 1 kg | 60 | mg/1000cy | SABIC method |
| Tensile Stress, yield, 50 mm/min | 20 | MPa | ISO 527 |
| Tensile Stress, break, 50 mm/min | 25 | MPa | ISO 527 |
| Tensile Strain, yield, 50 mm/min | 15 | % | ISO 527 |
| Tensile Strain, break, 50 mm/min | 110 | % | ISO 527 |
| Tensile Modulus, 1 mm/min | 590 | MPa | ISO 527 |
| Flexural Stress, yield, 2 mm/min | 20 | MPa | ISO 178 |
| Flexural Stress, break, 2 mm/min | 18 | MPa | ISO 178 |
| Flexural Modulus, 2 mm/min | 470 | MPa | ISO 178 |
| Tensile Stress, yld, Type I, 50 mm/min | 28 | MPa | ASTM D638 |
| Tensile Strain, brk, Type I, 50 mm/min | 100 | % | ASTM D638 |
| Flexural Modulus, 2.6 mm/min, 100 mm span | 380 | MPa | ASTM D790 |
| Taber Abrasion, CS-17, 1 kg | 26 | mg/1000cy | ASTM D1044 |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|----------------|-------------------------|-------------------|
| IMPACT | | | |
| Izod Impact, unnotched 80*10*4 +23°C | NB | kJ/m ² | ISO 180/1U |
| Izod Impact, unnotched 80*10*4 -30°C | NB | kJ/m ² | ISO 180/1U |
| Izod Impact, notched 80*10*4 +23°C | 25 | kJ/m ² | ISO 180/1A |
| Izod Impact, notched 80*10*4 -30°C | 15 | kJ/m ² | ISO 180/1A |
| THERMAL | | | |
| CTE, 23°C to 80°C, flow | 1.1E-04 | 1/°C | ISO 11359-2 |
| CTE, 23°C to 80°C, xflow | 9.E-05 | 1/°C | ISO 11359-2 |
| Ball Pressure Test, 75°C +/- 2°C | PASSES | - | IEC 60695-10-2 |
| Vicat Softening Temp, Rate B/50 | 75 | °C | ISO 306 |
| Vicat Softening Temp, Rate B/120 | 78 | °C | ISO 306 |
| PHYSICAL | | | |
| Mold Shrinkage, flow | 1.35 | % | SABIC method |
| Mold Shrinkage, xflow | 1.43 | % | SABIC method |
| Mold Shrinkage on Tensile Bar, flow | 1.2 – 1.4 | % | SABIC method |
| Density | 1.18 | g/cm ³ | ISO 1183 |
| Water Absorption, (23°C/saturated) | 0.5 | % | ISO 62-1 |
| Melt Volume Rate | | | |
| 320°C/2.16 kg | 8 | cm ³ /10 min | ISO 1133 |
| Specific Gravity | 1.18 | - | ASTM D792 |
| Moisture Absorption (est) | 0.3 | % | ASTM D570 |
| Melt Flow Rate, 295°C/6.6 kgf | 12 | g/10 min | ASTM D1238 |
| Matrix Tg | 168 | °C | DMA |
| Halogen Content | 0 | % | SABIC method |
| ELECTRICAL | | | |
| Volume Resistivity | 4.7E+14 | Ω.cm | IEC 60093 |
| Surface Resistivity, ROA | 1.E+15 | Ω | IEC 60093 |
| Dielectric Strength, in oil, 3.2 mm | 19 | kV/mm | IEC 60243-1 |
| Relative Permittivity, 100 Hz | 3 | - | IEC 60250 |
| Dissipation Factor, 100 Hz | 0.0091 | - | IEC 60250 |
| Volume Resistivity | 4.1E+16 | Ω.cm | ASTM D257 |
| Surface Resistivity | 1.E+15 | Ω | ASTM D257 |
| Dielectric Strength, in air, 3.2 mm | 16.1 | kV/mm | ASTM D149 |
| Dielectric Strength, in oil, 3.2 mm | 16.3 | kV/mm | ASTM D149 |
| Relative Permittivity, 50/60 Hz | 3.01 | - | ASTM D150 |
| Relative Permittivity, 100 kHz | 2.7 | - | ASTM D150 |
| Dissipation Factor, 50/60 Hz | 0.01 | - | ASTM D150 |
| Dissipation Factor, 100 kHz | 0.0056 | - | ASTM D150 |
| Comparative Tracking Index | 175 | V | IEC 60112 |
| FLAME CHARACTERISTICS | | | |
| UL Compliant, 94V-1 Flame Class Rating | 1.6 | mm | UL 94 by SABIC-IP |
| Glow Wire Flammability Index 960°C, passes at | 3.2 | mm | IEC 60695-2-12 |
| Oxygen Index (LOI) | 48 | % | ISO 4589 |
| OSU peak heat release rate (5 minute test) | 140 | kW/m ² | FAR 25.853 |
| Oxygen Index (LOI) | 46 | % | ASTM D2863 |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--------------------------------------|----------------|----------|--------------|
| COMBUSTION CORROSIVITY | | | |
| Corrosion, 1 hr (2500 angstroms max) | 40 | angstrom | ASTM E5.2170 |
| Corrosion, 24 hrs | 122 | angstrom | ASTM E5.2170 |
| Corrosion, 6 days | 183 | angstrom | ASTM E5.2170 |
| INJECTION MOLDING | | | |
| Drying Temperature | 100 – 110 | °C | |
| Drying Time | 6 | Hrs | |
| Maximum Moisture Content | 0.02 | % | |
| Melt Temperature | 300 – 320 | °C | |
| Nozzle Temperature | 300 – 320 | °C | |
| Front - Zone 3 Temperature | 295 – 315 | °C | |
| Middle - Zone 2 Temperature | 295 – 315 | °C | |
| Rear - Zone 1 Temperature | 295 – 315 | °C | |
| Mold Temperature | 65 – 95 | °C | |
| Back Pressure | 0.3 – 0.7 | MPa | |
| Screw Speed | 50 – 100 | rpm | |
| Shot to Cylinder Size | 40 – 60 | % | |
| Vent Depth | 0.025 – 0.076 | mm | |
| PROFILE EXTRUSION | | | |
| Barrel - Zone 1 Temperature | 280 – 290 | °C | |
| Barrel - Zone 2 Temperature | 300 – 310 | °C | |
| Barrel - Zone 3 Temperature | 310 – 320 | °C | |
| Barrel - Zone 4 Temperature | 310 – 325 | °C | |
| Hopper Temperature | 60 – 100 | °C | |
| Adapter Temperature | 315 – 325 | °C | |
| Die Temperature | 300 – 320 | °C | |
| Calibrator Temperature | 60 – 80 | °C | |

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.