

LNPTM LUBRICOMPTM COMPOUND 2X00858

PDX-FP-F-00858

DESCRIPTION

LN LUBRICOMP 2X00858 is a compound based on FEP resin containing proprietary fillers. Wear Resistant

TYPICAL PROPERTY VALUES

Revision 20200422

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	14	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	12	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	5.5	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	9.3	%	ASTM D 638
Tensile Modulus, 50 mm/min	1010	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	20	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	790	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	14	MPa	ISO 527
Tensile Stress, break, 5 mm/min	13	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	6.1	%	ISO 527
Tensile Strain, break, 5 mm/min	9.3	%	ISO 527
Tensile Modulus, 1 mm/min	930	MPa	ISO 527
Flexural Stress	19	MPa	ISO 178
Flexural Modulus, 2 mm/min	870	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	981	J/m	ASTM D 4812
Izod Impact, notched, 23°C	683	J/m	ASTM D 256
Izod Impact, unnotched 80*10*4 +23°C	84	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	31	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	79	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	57	°C	ASTM D 648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	80	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	61	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	2.17	-	ASTM D 792
Density	2.17	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.01	%	ASTM D 570
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating ⁽¹⁾	1.5	mm	UL 94 by SABIC-IP

(1) UL rating shown here is based on internal measurements.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.