

VALOX™ RESIN V8090

REGION EUROPE

DESCRIPTION

VALOX V8090 is a 50% glass fibre reinforced, PBT+PET blend with good surface finish. Applications: EV-Back plates, appliance housings, door handles, mirror brackets.

TYPICAL PROPERTY VALUES

Revision 20241205

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 5 mm/min	180	MPa	ISO 527
Tensile Stress, break, 5 mm/min	180	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	1.6	%	ISO 527
Tensile Strain, break, 5 mm/min	1.6	%	ISO 527
Tensile Modulus, 1 mm/min	18500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	270	MPa	ISO 178
Flexural Stress, break, 2 mm/min	265	MPa	ISO 178
Flexural Modulus, 2 mm/min	17000	MPa	ISO 178
Tensile Stress, yld, Type I, 5 mm/min	175	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	175	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	1.5	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	1.5	%	ASTM D638
Tensile Modulus, 5 mm/min	18500	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	250	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	250	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	17000	MPa	ASTM D790
IMPACT			
Izod Impact, notched 80*10*4 +23°C	12	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	60	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	11	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	62	kJ/m ²	ISO 179/1eU
Izod Impact, notched, 23°C	85	J/m	ASTM D256
Izod Impact, unnotched, 23°C	850	J/m	ASTM D4812
THERMAL			
Vicat Softening Temp, Rate A/50	223	°C	ISO 306
Vicat Softening Temp, Rate B/50	212	°C	ISO 306
Vicat Softening Temp, Rate B/120	212	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	210	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	225	°C	ISO 75/Bf
CTE, 23°C to 150°C, flow	1.25E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	1.15E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	223	°C	ASTM D1525
CTE, 23°C to 150°C, flow	1.25E-05	1/°C	ASTM E831

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, 23°C to 150°C, xflow	1.15E-04	1/°C	ASTM E831
PHYSICAL			
Density	1.77	g/cm³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.05	%	ISO 62
Water Absorption, (23°C/saturated)	0.16	%	ISO 62-1
Mold Shrinkage, flow, 24 hrs	0.05 – 0.45	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.75 – 1.15	%	ISO 294
Melt Volume Rate, MVR at 265°C/5.0 kg	20	cm³/10 min	ISO 1133
Melt Viscosity			
260°C, 1500 sec-1	230	Pa-s	ISO 11443
270°C, 1500 sec-1	195	Pa-s	ISO 11443
280°C, 1500 sec-1	155	Pa-s	ISO 11443
Specific Gravity	1.77	-	ASTM D792
Filler Content	50	%	ASTM D229
Moisture Absorption, (23°C/50% RH/24 hrs)	0.05	%	ASTM D570
Water Absorption, (23°C/24hrs)	0.14	%	ASTM D570
Mold Shrinkage, flow, 24 hrs	0.05 – 0.45	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs	0.75 – 1.15	%	ASTM D955
Melt Flow Rate, 265°C/2.16kgf	36	g/10 min	ASTM D1238
ELECTRICAL			
Comparative Tracking Index	275	V	IEC 60112
FLAME CHARACTERISTICS			
UL Compliant, 94HB Flame Class Rating	0.75	mm	UL 94 by SABIC-IP
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 285	°C	
Nozzle Temperature	265 – 275	°C	
Front - Zone 3 Temperature	260 – 280	°C	
Middle - Zone 2 Temperature	255 – 280	°C	
Rear - Zone 1 Temperature	240 – 260	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	60 – 110	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.