

LEXAN™ COPOLYMER XHT4143

REGION ASIA

DESCRIPTION

XHT4143 is a high flow, UV stabilized, high heat polycarbonate copolymer blend with an HDT/Af of 162C. It is available in a range of opaque and limited transparent colors.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	77	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	69	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	7	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	50	%	ASTM D 638
Tensile Modulus, 5 mm/min	2730	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	120	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2600	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	78	MPa	ISO 527
Tensile Stress, break, 50 mm/min	67	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	7	%	ISO 527
Tensile Strain, break, 50 mm/min	50	%	ISO 527
Tensile Modulus, 1 mm/min	2750	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2600	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	93	J/m	ASTM D 256
Izod Impact, notched, -30°C	76	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	72	J	ASTM D 3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	10	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	8	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	11	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	9	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	183	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	174	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	165	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.E-05	1/°C	ISO 11359-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Ball Pressure Test, 165°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	183	°C	ISO 306
Vicat Softening Temp, Rate B/120	181	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	173	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	162	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.6 – 0.95	%	SABIC method
Melt Flow Rate, 330°C/2.16 kgf	25	g/10 min	ASTM D 1238
Density	1.21	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.33	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.25	%	ISO 62
Melt Volume Rate, MVR at 330°C/2.16kg	24	cm ³ /10 min	ISO 1133
FLAME CHARACTERISTICS			
Glow Wire Flammability Index 850°C, passes at	2	mm	IEC 60695-2-12
Glow Wire Flammability Index 960°C, passes at	2.5	mm	IEC 60695-2-12
INJECTION MOLDING			
Drying Temperature	135	°C	
Drying Time	4 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	300 – 315	°C	
Nozzle Temperature	295 – 310	°C	
Front - Zone 3 Temperature	300 – 315	°C	
Middle - Zone 2 Temperature	290 – 305	°C	
Rear - Zone 1 Temperature	280 – 295	°C	
Mold Temperature	95 – 130	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 90	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.08	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.