

ULTEM™ RESIN D9065

REGION ASIA

DESCRIPTION

Polyetherimide blend. Meets FAR 25.853 and OSU 65/65 with low toxicity, smoke, and flame evolution. ECO Conforming.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	88	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	88	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	100	%	ASTM D 638
Tensile Modulus, 5 mm/min	3100	MPa	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	124	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	3100	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	149	J/m	ASTM D 256
Izod Impact, notched, -30°C	96	J/m	ASTM D 256
Izod Impact, Reverse Notched, 3.2 mm	2029	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	67	J	ASTM D 3763
Instrumented Impact Energy @ peak, -30	58	J	ASTM D 3763
PHYSICAL			
Specific Gravity	1.32	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 337°C/6.6 kgf	15.6	g/10 min	ASTM D 1238
FLAME CHARACTERISTICS			
OSU total heat release (2 minute test)	10	kW-min/m ²	FAR 25.853
OSU peak heat release rate (5 minute test)	50	kW/m ²	FAR 25.853
INJECTION MOLDING			
Drying Temperature	135	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	24	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	340 – 360	°C	
Nozzle Temperature	330 – 355	°C	
Front - Zone 3 Temperature	340 – 360	°C	
Middle - Zone 2 Temperature	325 – 350	°C	
Rear - Zone 1 Temperature	315 – 340	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.