

LEXANT™ RESIN 123

REGION ASIA

DESCRIPTION

UL rated HB as of 10/97. 200 series recommended when V-2 rating required. Nonhalogenated. 17.5 MFR, for small, intricate parts. UV stabilized.

TYPICAL PROPERTY VALUES

Revision 20180906

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	65	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	7	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	93	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2340	MPa	ASTM D 790
Hardness, Rockwell M	70	-	ASTM D 785
Hardness, Rockwell R	118	-	ASTM D 785
Taber Abrasion, CS-17, 1 kg	10	mg/1000cy	ASTM D 1044
IMPACT			
Izod Impact, unnotched, 23°C	3204	J/m	ASTM D 4812
Izod Impact, notched, 23°C	694	J/m	ASTM D 256
Tensile Impact, Type S	546	kJ/m ²	ASTM D 1822
Falling Dart Impact (D 3029), 23°C	169	J	ASTM D 3029
THERMAL			
Vicat Softening Temp, Rate B/50	154	°C	ASTM D 1525
HDT, 0.45 MPa, 6.4 mm, unannealed	137	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	132	°C	ASTM D 648
CTE, -40°C to 95°C, flow	6.84E-05	1/°C	ASTM E 831
Specific Heat	1.25	J/g·°C	ASTM C 351
Thermal Conductivity	0.19	W/m·°C	ASTM C 177
Relative Temp Index, Elec	100	°C	UL 746B
Relative Temp Index, Mech w/impact	100	°C	UL 746B
Relative Temp Index, Mech w/o impact	100	°C	UL 746B
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Specific Volume	0.83	cm ³ /g	ASTM D 792
Density	1.19	g/cm ³	ASTM D 792
Water Absorption, 24 hours	0.15	%	ASTM D 570
Water Absorption, equilibrium, 23C	0.35	%	ASTM D 570
Water Absorption, equilibrium, 100°C	0.58	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	17.5	g/10 min	ASTM D 1238
OPTICAL			
Light Transmission, 2.54 mm	88	%	ASTM D 1003

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Haze, 2.54 mm	1	%	ASTM D 1003
Refractive Index	1.586	-	ASTM D542
ELECTRICAL			
Volume Resistivity	>1.E+17	Ohm-cm	ASTM D 257
Dielectric Strength, in air, 3.2 mm	14.9	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	3.17	-	ASTM D 150
Relative Permittivity, 1 MHz	2.96	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.0009	-	ASTM D 150
Dissipation Factor, 1 MHz	0.01	-	ASTM D 150
Hot Wire Ignition {PLC}	4	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating	0.76	mm	UL 94
UV-light, water exposure /immersion	F1	-	UL 746C
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	280 – 305	°C	
Nozzle Temperature	275 – 300	°C	
Front - Zone 3 Temperature	280 – 305	°C	
Middle - Zone 2 Temperature	270 – 295	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.