

# VALOX™ RESIN 176

REGION ASIA

## DESCRIPTION

Unreinforced, neat PBT resin for fibers. Natural Color Only, Not intended for injection molding.

## TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	50	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	50	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	2	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	2	%	ASTM D 638
Tensile Modulus, 5 mm/min	2500	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	84	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2390	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	45	MPa	ISO 527
Tensile Stress, break, 50 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	1.8	%	ISO 527
Tensile Strain, break, 50 mm/min	1.8	%	ISO 527
Tensile Modulus, 1 mm/min	2600	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	81	MPa	ISO 178
Flexural Modulus, 2 mm/min	2290	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	890	J/m	ASTM D 4812
Izod Impact, notched, 23°C	28	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	5	J	ASTM D 3763
Izod Impact, unnotched 80°10'4 +23°C	35	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80°10'4 +23°C	2	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10'4 sp=62mm	7	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL</b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	104	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	48	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.5E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.5E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	178	°C	ISO 306
Vicat Softening Temp, Rate B/120	177	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80°10'4 sp=64mm	113	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80°10'4 sp=64mm	51	°C	ISO 75/Af
<b>PHYSICAL</b>			
Specific Gravity	1.32	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	1.5 – 1.8	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	1.6 – 2	%	SABIC method
Melt Flow Rate, 250°C/1.2 kgf	127	g/10 min	ASTM D 1238

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Viscosity	0	Pa-s	SABIC method
Density	1.31	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/sat)	0.08	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62
Melt Volume Rate, MVR at 250°C/ 1.2 kg	127	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 250°C/2.16 kg	231	cm <sup>3</sup> /10 min	ISO 1133
<b>COMPOUNDING EXTRUSION</b>			
Drying Temperature	110 – 120	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0	%	
Melt Temperature	245 – 260	°C	
Barrel - Zone 1 Temperature	200 – 230	°C	
Barrel - Zone 2 Temperature	240 – 255	°C	
Barrel - Zone 3 Temperature	240 – 275	°C	
Barrel - Zone 4 Temperature	240 – 275	°C	
Adapter Temperature	240 – 275	°C	
Die Temperature	240 – 275	°C	
Waterbath Temperature	25 – 35	°C	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.