

NORYL™ RESIN FP3060

REGION EUROPE

DESCRIPTION

NORYL FP3060 is an unfilled, injection moldable modified polyphenylene ether resin. Designed for good dimensional stability and high flow, this resin also uses non-chlorinated, non-brominated FR additives to achieve a V1 UL94 rating at 1.5 mm and VO@ 2.5mm with a specific density of 1.1 g/cm³. NORYL FP3060 may be an excellent material candidate for Flat Panel TV enclosure applications requiring good rheological properties, heat resistance, hydrolysis resistance, low density and thin wall flame resistance.

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	54	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	55	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	3	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	12	%	ASTM D 638
Tensile Modulus, 50 mm/min	2200	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	84	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2400	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	55	MPa	ISO 527
Tensile Stress, break, 50 mm/min	42	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3	%	ISO 527
Tensile Strain, break, 50 mm/min	11	%	ISO 527
Tensile Modulus, 1 mm/min	2420	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	82	MPa	ISO 178
Flexural Modulus, 2 mm/min	2530	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	78	J/m	ASTM D 256
Izod Impact, notched 80°10°4 +23°C	6	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10°4 -30°C	5	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	6	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	105	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	80	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.3E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	8.3E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	91	°C	ISO 306
Vicat Softening Temp, Rate B/120	93	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80°10°4 sp=64mm	74	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.1	-	ASTM D 792
Melt Flow Rate, 200°C/3.8 kgf	42	g/10 min	ASTM D 1238

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Density	1.1	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.13	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.02	%	ISO 62
Melt Volume Rate, MVR at 280°C / 1.2 kg	20	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 280°C/2.16 kg	41	cm ³ /10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Recognized, 94V-1 Flame Class Rating	1.5	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	2.5	mm	UL 94
INJECTION MOLDING			
Drying Temperature	65 – 75	°C	
Drying Time	2 – 3	hrs	
Melt Temperature	250 – 285	°C	
Nozzle Temperature	240 – 270	°C	
Front - Zone 3 Temperature	250 – 285	°C	
Middle - Zone 2 Temperature	230 – 260	°C	
Rear - Zone 1 Temperature	200 – 220	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	40 – 65	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.