

# NORYL GTX™ RESIN GTX870

REGION ASIA

## DESCRIPTION

NORYL GTX870 resin is a 20% glass reinforced alloy of Polyphenylene Ether (PPE) + Polyamide (PA). This injection moldable grade exhibits high stiffness, excellent chemical resistance, and high heat resistance. NORYL GTX870 resin is an excellent candidate for a wide variety of applications including electrical connectors and electronic base stations.

## TYPICAL PROPERTY VALUES

Revision 20241015

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yield	117	MPa	SABIC - Japan Method
Tensile Stress, yld, Type I, 5 mm/min	122	MPa	ASTM D638
Tensile Strain, break	12	%	SABIC - Japan Method
Tensile Strain, brk, Type I, 5 mm/min	5	%	ASTM D638
Flexural Stress	166	MPa	ASTM D790
Flexural Modulus	5680	MPa	ASTM D790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	117	J/m	ASTM D256
<b>THERMAL</b>			
HDT, 1.82 MPa, 6.4 mm, unannealed	200	°C	ASTM D648
CTE, -30°C to 30°C	0.00004 – 0.00006	1/°C	TMA
<b>PHYSICAL</b>			
Specific Gravity	1.24	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.5	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.8	%	SABIC method
<b>INJECTION MOLDING</b>			
Drying Temperature	95 – 105	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.07	%	
Melt Temperature	280 – 305	°C	
Nozzle Temperature	280 – 305	°C	
Front - Zone 3 Temperature	275 – 305	°C	
Middle - Zone 2 Temperature	270 – 305	°C	
Rear - Zone 1 Temperature	265 – 305	°C	
Mold Temperature	75 – 120	°C	
Back Pressure	0.3 – 1.4	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 50	%	
Vent Depth	0.013 – 0.038	mm	



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.