

LEXAN™ COPOLYMER CFR7630

REGION ASIA

DESCRIPTION

LEXAN CFR7630 Polycarbonate (PC) resin is a non-filled resin, suitable for injection molding and extrusion. This non-chlorinated, non-brominated flame retardant PC has an UL-94 V0 rating at 1.0 mm / 5VA rating at 3.0mm and is UV stabilized (F1 rating) providing additional weathering capability. LEXAN CFR7630 resin is available in transparent and opaque colors.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	68	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	52	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	51	%	ASTM D 638
Tensile Modulus, 50 mm/min	2500	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	106	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2400	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	67	MPa	ISO 527
Tensile Stress, break, 50 mm/min	52	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	23	%	ISO 527
Tensile Modulus, 1 mm/min	2400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	103	MPa	ISO 178
Flexural Modulus, 2 mm/min	2500	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	NB	J/m	ASTM D 4812
Izod Impact, unnotched, -30°C	NB	J/m	ASTM D 4812
Izod Impact, notched, 23°C	100	J/m	ASTM D 256
Izod Impact, notched, -30°C	85	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	66	J	ASTM D 3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	10	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	9	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	10	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	9	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	136	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	131	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	120	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.6E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.E-05	1/°C	ASTM E 831

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, 23°C to 80°C, flow	7.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.6E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	Pass	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	137	°C	ISO 306
Vicat Softening Temp, Rate B/120	139	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	131	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	120	°C	ISO 75/Ae
Relative Temp Index, Elec	125	°C	UL 746B
Relative Temp Index, Mech w/impact	120	°C	UL 746B
Relative Temp Index, Mech w/o impact	125	°C	UL 746B
PHYSICAL			
Specific Gravity	1.19	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.55 – 0.75	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.6 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	5	g/10 min	ASTM D 1238
Density	1.2	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.14	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.11	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	5	cm ³ /10 min	ISO 1133
OPTICAL			
Light Transmission at 1.0 mm	>90	%	SABIC method
Light Transmission at 2.0 mm	>89	%	SABIC method
Light Transmission at 3.0 mm	>88.0	%	SABIC method
ELECTRICAL			
Dielectric Constant (Dk), 1.1 GHz	2.79	-	ASTM ES 7-83
Dissipation Factor (Df), 1.1 GHz	0.0058	-	ASTM ES 7-83
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating	1	mm	UL 94
UL Recognized, 94-5VA Rating	3	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	875	°C	IEC 60695-2-13
Oxygen Index (LOI)	45	%	ISO 4589
UV-light, water exposure/immersion	F1	-	UL 746C
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	290 – 310	°C	
Nozzle Temperature	280 – 305	°C	
Front - Zone 3 Temperature	290 – 310	°C	
Middle - Zone 2 Temperature	275 – 300	°C	
Rear - Zone 1 Temperature	265 – 290	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.