

LNPTM THERMOCOMPTM COMPOUND ZX08005

ZX08005

DESCRIPTION

LNP THERMOCOMP ZX08005 is a Compound based on PPE + PS Blend resin, containing Mineral. Added features include: Improved Dielectric Properties.

TYPICAL PROPERTY VALUES

Revision 20200211

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 5 mm/min	55	MPa	ISO 527
Tensile Strain, break, 5 mm/min	4.4	%	ISO 527
Tensile Modulus, 1 mm/min	3400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	105	MPa	ISO 178
Flexural Modulus, 2 mm/min	4600	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	17	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	140	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	130	°C	ASTM D 648
PHYSICAL			
Density	2.07	g/cm ³	ISO 1183
ELECTRICAL			
Relative Permittivity, 100 MHz	6.58	-	IEC 60250
Relative Permittivity, 500 MHz	6.47	-	IEC 60250
Relative Permittivity, 1 GHz	6.16	-	IEC 60250
Dissipation Factor, 500 MHz	0.001	-	IEC 60250
Dissipation Factor, 1 GHz	0.001	-	IEC 60250
Dissipation Factor, 100 MHz	0.001	-	IEC 60250
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	4	hrs	
Melt Temperature	300 – 305	°C	
Front - Zone 3 Temperature	300 – 310	°C	
Middle - Zone 2 Temperature	290 – 300	°C	
Rear - Zone 1 Temperature	275 – 290	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.